


Product Code and Description


 Sorajet Tartrazine Liquid
Sorajet Tartrazine Concentrate

 Sorajet Yellow BRJ Liquid
Sorajet Yellow 86P
Sorajet Yellow BRD

 Sorajet Yellow GGN-C Liquid

 Sorajet Yellow 3GF Liquid

 Sorajet Gold RB Liquid


 Sorajet Rhodamine B Crude
Sorajet Rhodamine B Liquid

 Sorajet Red 8BLP 150% Liquid

 Sorajet Red 24 Liquid

Product Code and Description

 Sorajet Red MW-Feb/I

 Sorajet Red 195 Crude
Sorajet Red 195 Liquid

 Sorajet Blue FGND Crude
Sorajet Blue FGND Liquid

 Sorajet Cyan 199 Crude
Sorajet Bond Blue FBLK Liquid

 Sorajet Black 34 Liquid

 Sorajet Black 38 Liquid

 Sorajet Special Black .2M Liquid

Shades represented in this card are intended as a guide for basic color selection. These shades may vary based on the user's final formulation and/or substrate. Please contact First Source Worldwide, LLC for any additional technical assistance.


**Your first source
solution for
SoraJet
ink jet dyes**



**Corporate:
1524 S. Commercial Street
Neenah, WI 54956-4802**

**Lab/Manufacturing:
11725 W. Fairview Ave.
Milwaukee, WI 53226-3948**

**Phone: 920-886-0444
Fax: 920-886-1424
Email: fsw@fsw.cc
Web Site: www.fsw.cc**

www.fsw.cc	 Dyes & Pigments	Light Fastness	Nominal Strength	Chlorides	Chlorides Test @ 1 or 10%	pH	Surface Tension	Spectro Peak
	SoraJet Tartrazine Liquid	4	100%	<500	10%	3.4	>50	427
	SoraJet Tartrazine Concentrate	4	170%	<580	1%	7.0	>50	427
	SoraJet Yellow BRJ Liquid	7	100%	<200	10%	8.0	>50	384
	SoraJet Yellow 86P	7	500%	<100	1%	7.5	>50	384
	SoraJet Yellow BRD	7	500%	<200	1%	7.5	>40	384
	SoraJet Yellow GGN-C Liquid	6	100%	<400	10%	9.0	>50	404
	SoraJet Yellow 3GF Liquid	5	100%	<200	10%	9.0	>50	404
	SoraJet Gold RB Liquid	4	100%	<1400	10%	7.5	>50	425

	SoraJet Rhodamine B Crude	3	500%	<500	1%	7.0	>50	566
	SoraJet Rhodamine B Liquid	3	100%	<1000	10%	7.0	>40	566
	SoraJet Red 8BLP 150% Liquid	4	150%	<140	10%	7.5	>50	510
	SoraJet Red 24 Liquid	6	100%	<150	10%	7.5	>40	536
	SoraJet Red MW-FEB/I	6	100%	<200	1%	4.5	>40	540
	SoraJet Red 195 Crude	5	200%	<150	1%	6.0	>40	542
	SoraJet Red 195 Liquid	5	100%	<300	10%	5.0	>45	542

	SoraJet Blue FGND Crude	3	240%	<500	1%	5.0	>50	630
	SoraJet Blue FGND Liquid	3	100%	<450	10%	7.0	>50	630
	SoraJet Cyan 199 Crude	6	570%	<110	1%	5.5	>45	608
	SoraJet Bond Blue FBLK Liquid	6	100%	<500	10%	5.5	>45	608

	SoraJet Black 34 Liquid	3	100%	<500	10%	8.5	>50	575
	SoraJet Black 38 Liquid	3	100%	<500	10%	8.5	>50	553
	SoraJet Black RI Liquid	3	100%	<500	10%	8.5	>50	573
	SoraJet Black BF Liquid	3	100%	<500	10%	8.6	>50	575
	SoraJet Black SP Liquid	3	100%	<500	10%	8.5	>50	574
	SoraJet Special Black .2M Liquid	3	100%	<300	10%	7.5	>50	570
	SoraJet Special Black SP Liquid	3	100%	<100	10%	7.5	>50	570
	SoraJet Carbon Black Dispersion	7-8	100%	NA	NA	7.5	>50	NA
	SoraJet Carbon Black 1376	7-8	100%	NA	NA	7.5	>50	NA